

Remover for AR Resists

AR-P 600-70, 600-71, 300-76, 300-70, 300-72, 300-73 remover

For the stripping of tempered photoresist and e-beam resist films

Characterisation

- aqueous-alkaline solution (AR 300-73) or organic solvents (all others)

Remover recommendations after tempering:

- photoresists up to 180 °C: AR 600-71, 300-76
- photoresists up to 200 °C: AR 300-76, 300-71
- PMMAs up to 200 °C: AR 600-71, 300-76
- copolymers up to 210 °C: AR 600-71, 300-76
- CSAR 62 up to 200 °C: AR 600-71, 300-76
- novolac e-beam resists 150 °C: AR 300-73, 300-76

Properties

Parameter / AR	600-70	600-71	300-76 new	300-70, -72	300-73
Main component	acetone	dioxolane	DMG	NEP	TMAH
Density at 20 °C (g/cm ³)	0.79	1.02	1.08	1.03	1.00
Non-volatiles max. (%)	0.002				
Flash point (°C)	-17	3	103	98	-
Filtration (µm)	0.2				
Storage up to 6 month (°C)	10-22	10-18	15-25	10-22	10-22

Remover recommendations

 optimally suitable
 suitable
 limited suitability
 unsuitable

Properties / Remover AR	600-70	600-71	300-76 new * heated to 80 °C	300-70, 300-72 * heated to 80 °C	300-73 + heated to 50 °C
average time for removal at 1.5 µm					
Suitability for tempered photoresist films (21 °C)	inexpensive, commonly used	efficient all-rounder	universal, replacing the reprod. toxic, NEP: = AR 300-70, -72	universal, especially for thin films, but toxic for reproduction	special: AR-BR 5400, AR-P 3100, 3500, 3700
120 °C	15 s	10 s	25 s	20 s	30 s
150 °C	20 s	15 s	3 min 25 s *	2 min 20 s *	2 min 60 s +
180 °C	5 min	4 min	2 h 60 s *	2 h 50 s *	2 h 2 min +
200 °C			30 min *	25 min *	30 min +
Suitability for tempered e-beam resist films (21 °C)	inexpensive, commonly used	efficient all-rounder	universal, replacing reprod. -toxic NEP:	universal, but toxic for reproduction	special: AR-N 7520, 7700
PMMA 150 °C	25 s	20 s	20 min 10 s *	18 min 10 s *	15 min +
PMMA 180 °C	2 min	2 min	30 min 30 s *	28 min 30 s *	25 min +
PMMA 200 °C	3 min	3 min	42 min 50 s *	40 min 50 s *	
Copolymer 190 - 210 °C	10 s	5 s		50 s *	20 min +
CSAR 62 150 °C		30 s		50 s *	10 min +
CSAR 62 180 - 200 °C		40 - 60 s		4 min *	15 - 25 min +
Novolac-based 85 - 120 °C	5 - 60 s except 7700	3 - 50 s except 7700	5 s * except 7520, 7700	5 s * except 7520, 7700	25 s - 3 min +
Novolac-based 150 °C	10 s - 9 min except 7520, 7700	5 s - 7 min except 7520, 7700	30 s * except 7520, 7700	10 s * except 7520, 7700	10 s - 50 min +

Processing instructions for removers

Substrates coated with resist are exposed to the effect of the remover by immersion (puddle or dip). To reduce the dissolution time for tempered layers, removers AR 300-70, 300-72 and 300-76 may be heated to up to 80 °C, remover AR 300-73 to up to 50 °C or megasond may be helpful in this case. It is recommended to rinse off the remover with DI water, clean remover or with a suitable thinner. A stripping of very hard-baked layers (> 220 °C) with remover is hardly possible any more. In this case, oxidizing acids or oxygen plasma may be used for stripping. Further detailed remover specifications for a large variety of resists are listed on the following pages.



Remover for AR Resists

E-Beam Resists

Remover recommendations < 20/60s optimally suitable < 5/30 min suitable < 1-6 h limited suitability ≥ 6 h unsuitable

Product AR	Film thickness (µm)	Tempering (°C)	Recom- mend.	600-70	600-71	300-76	300-70, 300-72		300-73		
				21 °C	21 °C	21 °C	80 °C	21 °C	80 °C	21 °C	50 °C
AR-P 3100 Example 3110	1.5	95 - 120	300-76 300-73 (300-72)	< 20 s	< 20 s	< 20 s		< 20 s		< 20 s	
		150		3 h	< 20 s		< 20 s		< 60 s		
		180		6 h	< 5 min	< 60 s	< 5 min	< 60 s	1 h	< 60 s	
		200				< 30 min	< 30 min	< 30 min	< 30 min		
AR-P 3200 Example 3220	10	95	600-71 300-76 300-73	< 20 s	< 20 s	< 20 s		< 20 s		< 5 min	< 60 s
		120		< 20 s	< 20 s	< 60 s		< 60 s		< 30 min	< 5 min
		150		< 60 s	< 20 s	< 5 min	< 60 s	< 5 min	< 60 s	< 30 min	< 5 min
		180			4 h	1 h	< 30 min	1 h	< 30 min	< 30 min	< 30 min
		200					1 h	1 h	1 h	2 h	
AR-P 3500 Example 3540	1.5	95 - 150	600-71 300-73 300-76	< 20 s	< 20 s	< 20 s		< 20 s		< 20 s	
		180		< 30 min	< 5 min	< 5 min	< 20 s	< 5 min	< 20 s	< 60 s	< 20 s
		200					< 1 h	< 1 h	3 h	< 30 min	
AR-P 3500T Example 3540T	1.5	95 - 120	600-71 300-76 (300-72)	< 20 s	< 20 s	< 20 s		< 20 s		< 20 s	
		150		4 h	< 5 min	< 60 s	< 20 s	< 5 min	< 20 s	< 30 min	< 5 min
		180				< 30 min	< 5 min		< 5 min	< 30 min	< 30 min
		200					1 h	1 h			
AR-P 3700 / 3800 Example 3740	1.5	95	600-71 300-76 300-73	< 20 s	< 20 s	< 20 s		< 20 s		< 60 s	
		120		< 20 s	< 20 s	< 20 s		< 20 s		< 5 min	< 20 s
		150		< 60 s	< 20 s	< 60 s		< 60 s		< 5 min	< 20 s
		180		< 30 min	< 30 min	< 5 min	< 60 s	< 5 min	< 60 s	< 30 min	< 60 s
		200					< 30 min	< 30 min	< 30 min	6 h	< 30 min
AR-P 5300 Example 5350	1.5	95 - 150	600-71 300-73 300-76	< 20 s	< 20 s	< 20 s		< 20 s		< 20 s	
		180		< 60 s	< 60 s	< 60 s		< 60 s		< 60 s	
		200					1 h	1 h	< 30 min		
AR-U 4000 Example 4040	1.5	95	600-71 300-76 (300-72)	< 20 s	< 20 s	< 20 s		< 20 s		< 20 s	
		120		< 20 s	< 20 s	< 20 s		< 20 s		< 60 s	
		150					< 5 min		< 5 min	< 30 min	3 h
		180					< 30 min		< 30 min		
AR-PC 500(0) Example 504	2.0	150	600-71 300-76 (300-72)	< 5 min	< 5 min	< 1 h	< 5 min	< 1 h	< 5 min	< 5 min	< 5 min
		190		< 30 min	< 30 min	1 h	< 5 min	1 h	< 5 min	< 5 min	4 h
AR-P 5900 Example 5910	5.0	85 - 120	300-76 300-73 (300-72)	< 20 s	< 20 s	< 20 s		< 20 s		< 5 min	
		150				< 2 h	< 30 min	< 2 h	< 30 min	< 2 h	< 5 min
		180								< 2 h	
		200									
AR-N 4200 Example 4240	1.5	85 - 150	600-71 300-76 300-73	< 20 s	< 20 s	< 20 s		< 20 s		< 20 s	
		180		< 20 s	< 20 s	< 60 s		< 60 s		< 5 min	
		200					< 1 h	< 1 h	< 1 h	< 1 h	

Remover for AR Resists

Remover recommendations				< 20/60 s	optimally suitable	< 5/30 min	suitable	< 1-6 h	limited suitability	≥ 6 h	unsuitable
Product AR	Film thickness (µm)	Tempering (°C)	Recom- mend.	600-70	600-71	300-76		300-70, 300-72		300-73	
				21 °C	21 °C	21 °C	80 °C	21 °C	80 °C	21 °C	50 °C
AR-N 4300 Example 4340	1.5	95	300-76 (300-72) 300-73	< 20 s	< 20 s	< 20 s		< 20 s		< 60 s	
		110				< 60 s		< 60 s	1 h	< 60 s	
		120				< 30 min	< 5 min	< 5 min		6 h	< 30 min
		150				1 h	< 30 min	< 30 min	< 5 min		< 30 min
		180				6 h	1 h	1 h	< 30 min		
		200						5 h	1 h		
AR-N 4400 Example 4400-50	50	95	600-71 600-70	< 20 s	< 20 s	< 5 min	< 5 min	< 5 min	< 60 s	< 60 s	
		120		< 5 min	< 5 min	6 h	< 60 s	5 h	< 60 s	6 h	< 30 min
		150		< 5 min	< 5 min		1 h		1 h		2 h
		180		< 30 min	< 30 min		2 h		2 h		
		200		5 h	4 h						
AR-P 617 Example 617.08	0.5	190	600-71 300-76 300-73	< 5 min	< 5 min	< 1 h	< 60 s	< 1 h	< 60 s		< 30 min
		210		< 30 min	< 5 min	6 h	< 5 min	6 h	< 5 min		< 30 min
AR-P 630-670 Example 671.05	0.5	150	600-71 300-76 (300-72)	< 20 s	< 20 s	< 30 min	< 20 s	< 30 min	< 20 s		< 30 min
		180		< 5 min	< 5 min	< 30 min	< 60 s	< 30 min	< 60 s		< 30 min
		200		< 5 min	< 5 min	< 1 h	< 60 s	< 1 h	< 60 s		
AR-P 6200 new Example 6200.09	0.4	150	600-71 300-76 300-73		< 20 s	< 30 min	< 5 min	< 30 min	< 5 min	< 30 min	< 5 min
		180			< 60 s	< 30 min	< 5 min	< 30 min	< 5 min	< 1 h	< 30 min
		200			< 60 s	< 30 min	< 60 s	< 30 min	< 60 s		< 30 min
AR-P 7400 Example 7400.23	1.5	105	600-71 300-76 (300-72)	< 20 s	< 20 s	< 20 s	< 20 s	< 20 s		< 20 s	
		120		< 20 s	< 20 s	< 20 s	< 20 s	< 20 s		< 20 s	
		150					< 5 min		< 5 min		3 h
		180					< 30 min		< 30 min		
AR-N 7500 Example 7500.18	0.4	85-150	600-71 300-76 300-73	< 20 s	< 20 s	< 20 s		< 20 s		< 20 s	
		180					6 h		4 h	3 h	< 10 min
AR-N 7520 new Example 7520.17	0.4	85	600-71 300-73 300-76	< 20 s	< 20 s	< 20 s		< 20 s	< 20 s	< 60 s	
		105		< 20 s	< 20 s	< 20 s		< 20 s	< 20 s	< 5 min	
		120					4 h		3 h	< 30 min	< 5 min
		150					6 h		4 h		< 1 h
AR-N 7700 Example 7700.18	0.4	105	300-76 300-73			< 1 h	< 30 s		< 1 h	< 1 h	< 60 s
		120								< 1 h	< 5 min
		150								3 h	< 30 min
AR-N 7720 Example 7720.18	1.4	105-120	600-71 300-76 (300-72)	< 60 s	< 60 s	< 20 s		< 20 s		< 20 s	
		150		< 5 min	< 5 min	3 h	< 5 min	2 h	< 5 min	< 60 s	
		180					< 30 min	< 30 min	< 30 min	< 30 min	< 5 min
		200					1 h		1 h		

The average times required for removal as listed under "properties" are divided into time clusters (< 20 s, < 60 s ...) for better orientation. In the column for remover recommendations, the first entry applies to low-baked and the second entry (or, if applicable, the third) to resist films baked at higher temperatures. The recommendation for remover AR 300-72 is indicated in brackets, since this remover is highly effective, but also classified as toxic for reproduction and thus not prioritized by Allresist. As replacement, we recommend the equivalent removers AR 300-76 and 600-71.